

**Powder SilkeMat® Rigidizer
INSTRUCTIONS**

- **Mix 1 part dry powder to 4 parts distilled (recommended) water, by volume, in a clean container.**
- **USE A DUST MASK WHEN MIXING.**
- **Mix well and let stand 12-24 hours**
- **Stir well and mix thoroughly with an electric hand blender if making up a large quantity. Otherwise, a whisk will suffice.**
- **Use a strainer to remove any unmixed particles. It is now reconstituted and ready to use.**
- **Keep container sealed and stir again before using, as the ingredients settle. Can be thinned with water.**

www.SilkeMat.com Greensboro NC 27401 USA